



Scandia 2000[®] Digital

Product sheet

Grammage	Thickness	Bulk	Roughness Bendtsen	Whiteness White	Whiteness Natural*	Opacity
g/m ²	µm	cm ³ /g	ml/min	CIE	CIE	%
80	100	1,25	250	148	80	92
90	113	1,25	250	148	80	93
100	125	1,25	250	148	80	94
115	144	1,25	250	148	80	95
130	163	1,25	250	148	80	96
150	188	1,25	250	148	80	97
170	213	1,25	250	148	80	>97
200	250	1,25	250	148	80	>97
240	300	1,25	250	148	80	>97
270	338	1,25	250	148	80	>97
300	375	1,25	250	148	80	>97

*Natural is manufactured without OBA



LESSEBO PAPER