



# Scandia 2000<sup>®</sup>

Product sheet

Grammage	Thickness	Bulk	Roughness Bendtsen	Whiteness White	Whiteness Natural*	Whiteness Ivory*	Opacity
g/m <sup>2</sup>	µm	cm <sup>3</sup> /g	ml/min	CIE	CIE	CIE	%
70	91	1,30	250	148	80	60	91
80	104	1,30	250	148	80	60	92
90	117	1,30	250	148	80	60	93
100	130	1,30	250	148	80	60	94
115	149	1,30	250	148	80	60	95
130	169	1,30	250	148	80	60	96
150	195	1,30	300	148	80	60	97
170	221	1,30	300	148	80	60	>97
200	260	1,30	300	148	80	60	>97
240	312	1,30	300	148	80	60	>97
270	351	1,30	300	148	80	60	>97
300	390	1,30	300	148	80	60	>97
350	455	1,30	300	148	80	60	>97
440	550	1,25	300	148	80	60	>97

\*Natural and Ivory are manufactured without OBA



**LESSEBO PAPER**