



Lessebo Design[®] Smooth

Product sheet

Grammage	Thickness	Bulk	Roughness Bendtsen	Whiteness UltraWhite	Whiteness Bright	Whiteness White	Whiteness Natural*	Whiteness Ivory*	Opacity
g/m ²	µm	cm ³ /g	ml/min	CIE	CIE	CIE	CIE	CIE	%
80	88	1,10	120	168	158	148	80	60	91
90	99	1,10	120	168	158	148	80	60	92
100	110	1,10	120	168	158	148	80	60	93
115	127	1,10	120	168	158	148	80	60	94
120	132	1,10	120	168	158	148	80	60	94
130	143	1,10	120	168	158	148	80	60	95
150	165	1,10	120	168	158	148	80	60	96
200	220	1,10	120	168	158	148	80	60	97
240	264	1,10	120	168	158	148	80	60	>97
270	297	1,10	120	168	158	148	80	60	>97
300	330	1,10	120	168	158	148	80	60	>97
350	385	1,10	120	168	158	148	80	60	>97
440	484	1,10	120	168	158	148	80	60	>97

* Natural and Ivory are manufactured without OBA



LESSEBO PAPER